



## GE Sealants & Adhesives

### Product Name:

**VIP8300 LAST-O-COAT TEXTURED ELASTOMERIC WATERPROOF COATING  
(VP8300, VP8320, VP8330)**

### Product Description

VIP8300 Last-O-Coat Textured Elastomeric Coating products are internally plasticized, high-build waterproof emulsion coatings made with modified acrylic resins providing a minimum of 300% elongation. VIP8300 Last-O-Coat Textured Elastomeric Coatings are available in Smooth and Textured in white and custom colors.

### Basic Uses

Uses: VIP8300 Last-O-Coat provide a flexible, long-lasting waterproof coating for use on exterior above-grade masonry, stucco, concrete block, poured and precast concrete, exterior insulation and finish systems (EIFS), brick, wood and metal.

### Technical Data

Property	Value	Test Method
% Solids by Weight	58.70 ± 2%	Lab Value
% Solids by Volume	49.20 ± 2%	Lab Value
Viscosity	K.U.'s 125 ± 5	Stormer
Freeze/Thaw Stability	5 Cycles	Lab Value
% Elongation (To break)	300%	ASTM D-2370-82
Shore A Hardness	80	ASTM D-2240-86
Tensile Strength	260 psi (1000 UV hrs.)	ASTM D-2370-82
Water Vapor Transmission	Permeance: 9.64 Perms	ASTM D-1653-85
Low Temperature	Passes 180° bend at 0°F	ASTM C-734-82
Mildew Resistance	No Growth	Fed. Test No.141B,6271
Mold Resistance	No Growth	ASTM D-3273/D-3274
VOC	VIP8320 52 g/L VIP8330 52 g/L VIP8300 52 g/L	Calculated

Typical product data values should not be used as specifications. Assistance is available by contacting GE Silicones at 1-800-228-5537.

### Limitations

- ⚡ Do not apply when the temperature is below 50°F.
- ⚡ Do not apply when relative humidity is above 90%.
- ⚡ Ambient temperature must be 5°F above dew point and rising.
- ⚡ Do not apply when there is a threat of rain.
- ⚡ Do not apply to surfaces with excessive moisture content.
- ⚡ This is a breathing coating designed to let moisture vapor escape.  
Do not use as a vapor barrier.

## Surface Preparation

### Surface Preparation:

**New:** The surface must be clean, sound, dry, free of any grease, dirt, oils, mildew, chalk, laitance, efflorescence, release agents, and other foreign materials. New masonry should cure 30 days prior to coating and have a pH of 11 or less. If the pH is higher than 11 after cure, the surface must be sealed with VIP1200 Acrylic Alkali-Resistant Surface Conditioner. Prior to applying VIP1200 Acrylic Alkali-Resistant Surface Conditioner, allow stucco and concrete block mortar to cure 3 days.

Poured-in-place precast concrete should be allowed to cure 7 days.

**Previously Coated:** Remove all loose, peeling or flaking coating. Remove mildew and all other contaminants that will interfere with adhesion. Spot-prime all bare wood or metal with an appropriate primer. If chalk remains after cleaning, the surface should be sealed with Surface Conditioner.

Always check for the new coating's adhesion to the previously painted surface by applying a test patch of 2-3 square feet. Allow to dry thoroughly; check adhesion by applying masking tape to a new coating and pull it off. If no coating is removed, good adhesion is assumed.

**Patching and Sealing:** All voids, cracks, cracked mortar joints, and meetings of dissimilar materials should be patched with VIP5000 Series Sealants. All exterior openings such as air conditioner openings, window and door surrounds, vents, electrical conduits, expansion and control joints, etc., should be sealed with VIP5780 Acrylic Urethane Elastomeric Sealant. Refer to VIP5000 technical data sheets for additional application information.

## Method of Application

Coating is ready for use. Do not thin. Material may be applied by airless spray, power roller or conventional roller. Surfaces that have been properly prepared are to receive a pinhole free application of VIP8100 to achieve the recommended dry film thickness.

**Power Roller:** Apply a liberal coat and check application with a wet film gauge to ensure that minimum wet film thickness is obtained. Backroll in a downward motion to ensure a uniform finish with the stipple all in one direction. Coverage rate will vary and is dependent upon the texture and profile of the surface. Dry film thickness of completed project is based 10-12 mils dry.

**Airless Spray:** Apply a liberal coat in a cross-hatch pattern, check film thickness with a wet film thickness gauge to ensure that minimum wet film thickness is obtained. Coverage will vary and is dependent upon the texture and profile of the surface. Dry film thickness of completed project is based 10-12 mils dry. Wear respiratory protection if exposure to vapor or mist from processing is possible.

**Conventional Roller:** Apply in two coats, check application with a wet film gauge to ensure that the minimum wet film thickness of each coat is obtained. Keep roller cover saturated with material at all times. Finish off with a dry roller in downward direction to ensure a uniform finish with the stipple all in one direction. Second coat should be applied when material is no longer tacky (4-6 hours).

Coverage will vary and is dependent upon the texture and profile of the surface. Dry film thickness of completed project is based on 10-12 mils dry.

### Application tips:

- ✧ Boxtint material.
- ✧ Maintain a wet edge during application.
- ✧ Apply in a manner to provide a pinhole free film.
- ✧ Contact manufacturer with any questions prior to application.

### Recommended Spread Rate & Coverage:

Spreading Rate:	10 mils DFT:	70 - 80 sq. ft./gal.
	15 mils DFT:	45 - 55 sq. ft./gal.
10 mils Dry Film Thickness:	Wet	20 - 24 mils.
	Dry	10 - 12 mils.
15 mils Dry Film Thickness:	Wet	30 - 36 mils.
	Dry	15 - 18 mils.

Packaging: 5 gallon pail.

When using, do not keep in direct sunlight for prolonged periods. KEEP FROM FREEZING.



## **Clean Up**

Clean all equipment immediately after use with warm, soapy water.

VIP8300 Textured Elastomeric Coating is available in the United States, through distributors.

Contact your local distributor or the nearest GE Technical Service Center for cost and availability information.

## **Handling and Safety**

**WARNING CANCER HAZARD.** This product contains greater than 0.1% crystalline silica. The International Agency for Research on Cancer (IARC) has determined that "there is sufficient evidence for the carcinogenicity of crystalline silica to experimental animals and limited evidence of carcinogenicity in humans."

Material Safety Data Sheets (MSDS) are available upon request from GE Sealants and Adhesives (GESA). Similar information for solvents and other chemicals used with GESA products should be obtained from your suppliers. When solvents are used, proper safety precautions must be observed. Do not breathe mist. Use only in well ventilated area. Wear respiratory protection if exposure to vapor or mist from processing is possible. **KEEP OUT OF REACH OF CHILDREN.**

## **Warranty**

GE Sealants & Adhesives warrants the performance of this product, provided it is properly stored and applied before the "use before" date shown. If not satisfied, return product and/or proof of purchase to address below and GE Sealants & Adhesives will, at its option, replace or refund the purchase price of this product. GE shall in no event be liable for any other damages in excess of the amount of the purchase price. **THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR DEFECTS IN, OR FAILURE OF, THIS PRODUCT, AND THE SOLE AND EXCLUSIVE LIABILITY OF GENERAL ELECTRIC COMPANY THEREFOR. THIS LIMITED WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES WRITTEN OR ORAL, STATUTORY, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF THE MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.**

Prior to considering use of a GE Sealants & Adhesives product in fulfilling any government requirement, please contact the Government and Trade Compliance Office at 413-448-4624

## **Legal Disclaimer**

THE MATERIALS, PRODUCTS AND SERVICES OF GE SILICONES, GE SEALANTS & ADHESIVES, GE BAYER SILICONES, GE TOSHIBA SILICONES, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions.

Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

VIP8300 (7/01)